



SANODURE® BLACK VA

Sanodure Black VA may be used as a base for black mixtures and as a shading component in a variety of color formulations. This dye has a purple cast when viewed in incandescent light.

Chemical description:	Azo dye (powder)
Light fastness:	5 – 6 (fair)
Heat fastness:	Good up to 250° F.

RECOMMENDED APPLICATION DETAILS:

Concentration:	10 g/l (for black)
pH range	4.5 - 6.0
Buffering:	Anodal® Dye Buffer Liquid
Temperature:	120° - 140° F.
Immersion time:	10 - 20 minutes for black

PREFERRED SEALING METHODS:

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

PRECAUTIONS:

Effective rinsing and normal care to eliminate drag-in are recommended.

ENVIRONMENTAL CONSIDERATIONS:

This RoHS compliant product contains chromium as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.