



SANODURE® BLACK WH

Sanodure Black WH is a general purpose dye suitable for all interior applications. Its solutions are stable and resistant to contamination by drag-in of sulfates. It is not recommended for exterior applications or other situations where it is subjected to intense UV radiation.

| | |
|-----------------------|------------------------|
| Chemical description: | Azo dye blend (powder) |
| Light fastness: | 5 – 6 (fair) |
| Heat fastness: | Good up to 250° F. |

RECOMMENDED APPLICATION DETAILS:

| | |
|-----------------|--------------------|
| Concentration: | 10 g/l (or higher) |
| pH range: | 4.5 - 6.0 |
| Buffering: | not required |
| Temperature: | 120° - 140° F. |
| Immersion time: | 10 to 30 minutes |

PREFERRED SEALING METHODS:

| | |
|---------|---|
| Hot: | Anodal ASL or Anodal AS |
| Medium: | Anodal MS-1 New or Anodal MTS Plus |
| Cold: | Anodal CS-2, Anodal CS-2N or Anodal CS3 |

PRECAUTIONS:

Effective rinsing and normal care to eliminate drag-in are recommended.

ENVIRONMENTAL CONSIDERATIONS:

This RoHS compliant product contains chromium as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.