



## SANODURE® COPPER BF

**Sanodure Copper BF** may be utilized to produce a wide range of shades varying from freshly polished copper to a brilliant orange suitable for safety warning symbols and similar applications where high visibility is of importance.

Chemical description:	Azo dye (powder)
Light fastness:	4 – 5 (fair)
Heat fastness:	Good up to 300° F.

### **RECOMMENDED APPLICATION DETAILS:**

Concentration:	0.5 - 5.0 g/l
pH range:	5.5 - 7.0
Buffering:	Anodal® Dye Buffer Liquid
Temperature:	120° - 140° F.
Immersion time:	2 - 20 minutes

### **PREFERRED SEALING METHODS:**

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

### **PRECAUTIONS:**

If the shade becomes too orange after extended use a correction may be made by adding *Sanodure Bordeaux RL*.

### **ENVIRONMENTAL CONSIDERATIONS:**

This RoHS compliant product contains chromium as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.