



SANODURE® MIL TAN 33446

Sanodure Mil Tan 33446 is a dye mixture that has been specially formulated to produce a military desert “tan” or “sand” shade for desert camouflage. The shade is often specified as MIL 595 33446.

Chemical description:	Azo dye blend (powder)
Light fastness:	6 (good)
Heat fastness:	Moderate up to 250° F.

RECOMMENDED APPLICATION DETAILS:

Concentration:	0.5 – 5.0 g/l
pH range:	5.0 – 6.0
Buffering:	Anodal® Dye Buffer Liquid
Temperature:	120° - 140° F.
Immersion time:	2 – 20 mintes

PREFERRED SEALING METHODS:

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

PRECAUTIONS:

This dye tends to shift towards yellow at higher pH values.

ENVIRONMENTAL CONSIDERATIONS:

This RoHS compliant product contains chromium as an integral part of the dye. The preferred method of disposal is described in the Reliant bulletin, the *Anodal WT System*.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.