



## SANODYE® GREEN AEN

*Sanodye Green AEN* produces an attractive emerald-green color. Although it is a mixture it has reasonable stability and long tank life.

### **PROPERTIES:**

Chemical description:	Azo dye blend (powder)
Light fastness:	Very good (6 – 7)
Heat fastness:	Good up to 250° F.

### **RECOMMENDED APPLICATION DETAILS:**

Concentration:	0.5 - 3.0 g/l
pH range:	5.5 - 6.0
Buffering:	~1% Ammonium Acetate Liq.
Temperature:	140° - 160° F.
Immersion time:	2 - 20 minutes

### **PREFERRED SEALING METHODS:**

Hot:	Anodal ASL or Anodal AS
Medium:	Anodal MS-1 New or Anodal MTS Plus
Cold:	Anodal CS-2, Anodal CS-2N or Anodal CS3

### **PRECAUTIONS:**

Algae or fungi growths may become a problem if the tank is not kept sterile by boiling the solution occasionally. Temperature control is needed to maintain shade. Adjustments may be made with additions of either *Sanodye Blue A* or *Yellow D*.

### **ENVIRONMENTAL CONSIDERATIONS:**

This is a RoHS compliant product that contains no heavy metals.

Recommendations, notices or instructions as to handling, use, storage or disposal of this product, including its use alone or in combination with other products, or as to any apparatus or process for its use are based upon information believed to be reliable. No liability is taken with respect to any such recommendations or instructions. Sole and exclusive warranty is that products comply with published chemical and physical specifications as provided on the certificate of analysis. No other warranties, either express or implied are given.